



Technical Data Sheet

Ecocrete 395 High-Range Water Reducing & Super plasticizing Concrete Admixture



Description

ECOCRETE 395 is versatile concrete admixture which impart a superior high performance to concrete properties. **ECOCRETE 395** has been developed to promote and enhance workability and slump retaining ability, while providing excellent durability and ultimate strength to concrete.

ECOCRETE 395 conform to the requirement of ASTM C494 type G, ASTM C 1017 and EN 934-2.

Application

- To increase workability retention of fresh concrete.
- To provide increased ultimate strength by reducing water demand in concrete mixes.
- To produce high quality concrete of improved durability by reducing permeability.

Advantages

- Higher strength with same cement content.
- Minimizing segregation problems by improving cohesion.
- Improved workability reduces placing and compaction problems.
- Cement saving without affecting strength.
- More durable concrete as a result of reduction in permeability and lower water to cement ratio.
- Chloride free.

Technical properties

Appearance and Color	Brown Liquid
Specific Gravity	1.20 ± 0.02
Total Chloride Content	Nil

Packaging

Available in bulk, 1000 Lt. Tote or in 210Lt. drums

Method of Use

Field Applications:

ECOCRETE 395 can be added to the mixing water prior to its addition to the aggregates or directly to the freshly mixed concrete (the plasticizing effect is more pronounced).

For ready Mix Concrete, **ECOCRETE 395** can be added to the concrete immediately prior to discharge and after further mixing has taken place for three minutes.

Dosage Rate

A dosage rate of 0.75 – 2.25% volume per weight of cementitious material.

It is recommended to carry out trial mixes to define the exact dosage rate required.

ECOCRETE 395 can be combined with other admixtures in our range, trial mixes are recommended to ensure design parameters are attained.

It is compatible with local cements and cementitious replacements.

Effects of overdosing:

When overdosing beyond the design limit occurs, the set retarding effects increases.

Overdose can result in excessive workability leading to segregation and bleeding.

During this period the concrete must be kept moist in order to prevent premature drying out.

However, the ultimate strength of the concrete will not be adversely affected as a result of over-dosage if the concrete is properly cured.

Storage

Ecocrete 395 shelf life is 6 months from date of manufacture.

Cleaning

In case of spillage, wash it with clean water.

Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.



Technical Data Sheet

Ecocrete 395 High-Range Water Reducing & Super plasticizing Concrete Admixture



Cautions

Health and safety

Ecocrete 395 is not a fire or health hazard. If however, it is spilled, the floor will become slippery and should be washed down with water immediately but should not be left to enter sewers/surface or ground water, in case of uncontrollable situation, wash it with plenty of water to dilute.

In case of eye contact or ingestion, seek medical attention without delay.

Do not dispose of into water or soil but according to local regulations.

Fire

Ecocrete 395 is non-flammable.



Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.