



Technical Data Sheet

Ecohard HBE 60 Solvent Free Epoxy Floor Coating

Description

Ecohard HBE 60 is high build, hard wearing solvent free self-primed epoxy flooring, designed to provide hard impact and abrasion resistance with an excellent coating for concrete floors.

Ecohard HBE 60 is suitable for use on floors and walls in production areas, hygienic clean rooms, high density traffic warehouses, workshops, car production facilities, showrooms, pharmaceutical industries, and as a traffic deck protection system.

It is ideally suited for use in wet areas where a high degree of chemical resistance is required such as dairies, soft drinks production, chemical manufacture etc.

Ecohard HBE60FG is a food grade epoxy flooring complying the requirements as per BSEN1186-9

Advantages

- Hard wearing: Durable, low maintenance costs
- High impact and abrasion resistance
- Fast application
- Easy to clean finish
- Chemical resistant: Proven against a wide range of industrial chemicals
- Does not support growth of bacteria, fungi or micro-organisms
- Available in wide range of colors to improve the working environment and identify slip hazard areas

Technical properties

Color	Variable
Solid content by volume	98% ± 2%
Compressive strength BSEN196-1	≥ 75MPa @ 7days
Flexural strength ASTM C579-18	≥ 35MPa @ 7days
Tensile strength BS6319-7	≥ 15MPa @ 7days
Bond Strength ASTM D4541	≥ 2Mpa (Concrete F)
Foot traffic:	24hours @ 20°C
vehicular traffic:	48 hours @ 20°C
Pot life	45 min @ 20°C
Full Cure	7 days@ 25°C

Method of use

Surface preparation

The substrate must be clean, dry, even, dense and free from oil, grease, dust and other contaminants.

A clean surface will ensure maximum adhesion between the substrate and the coating. Concrete floors must have a minimum compressive strength of 25N/mm² and a maximum concrete relative humidity of 80% (max. moisture content of 4%), relative humidity can be measured using a hygrometer. Concrete relative humidity should be less than 80% for concrete 28 days old or more.

Unsound layers and contaminated concrete surfaces must be prepared using mechanical surface removing equipment.

Acid etching can be used only in well ventilated areas.

Areas deeply contaminated by oil or grease, such areas should be treated by hot compressed air.

Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.



Technical Data Sheet

Ecohard HBE 60 Solvent Free Epoxy Floor Coating

Priming

High porosity surfaces should be primed with **Ecohard EP primer S**, a solvent based epoxy resin primer designed for maximum absorption and adhesion to concrete substrates. The primer should be allowed to cure for 24 hours. Use lamb's wool roller to apply the primer. More than one coat may be required for highly porous or textured surfaces.

Mixing

Prior to mixing, stir individual components of Resin and Hardener. Add the entire contents of the hardener container to the base and mix thoroughly for at least 3 minutes.

To avoid inconsistent workability and pot life, make sure that the materials to be used are stored in shaded area and protected from extremes of temperatures, for at least 24 hours prior to application.

Precaution: don't mix **Ecohard HBE 60** by hand as this could lead to areas of uncured material.

Application

Use brush or lamb's wool roller, or airless spray machine to apply the mixed **Ecohard HBE 60** onto the prepared surfaces.

To get a film thickness of 400 microns, apply 2 coats of **Ecohard HBE 60** at 5.0 m²/L per 200Micron coat, second coat should be applied at a right angle to the first coat. The second coat may be applied as soon as the first coat has initially dried. Drying time depend on the substrate and the ambient conditions.

If the over coating time is exceeded the first coat must be abraded with sand paper prior to the application of the second coat. Adequate ventilation must be provided to ensure that necessary drying and curing of the material is achieved.

Antislip application

The base coat should be applied at a minimum film thickness of 250 micron and then fully blinded with the chosen Antislip Aggregate. Once the base coat has reached initial cure, all excess aggregates should be removed before a further application of **Ecohard HBE 60** top coat.

The top coat should be applied at a minimum film thickness of 400 micron to 750 micron depending on Antislip Aggregate size used.

Theoretical Coverage

Approximately 5m²/L/coat

Storage

12 months when stored properly in unopened container in dry conditions at temperature between 10 - 25°C.

Cleaning

All tools shall be cleaned immediately after application using **Envirocon -Solvent**. Hardened materials must be cleaned mechanically.

Packaging

Ecohard HBE 60 is available in 24kg (16liter) Kit

Cautions

Health and safety

Avoid skin and eye contact by wearing overalls, gloves, goggles, and air-mask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water.

Avoid inhalation of vapors and paint mist by wearing suitable air-mask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area.

Smoking in the area should not be permitted. Local safety regulations should be followed.

Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.



Technical Data Sheet

Ecohard HBE 60 Solvent Free Epoxy Floor Coating

Fire

Ecohard HBE 60 is non-flammable.

E n v i r o c o n C o n s t r u c t i o n P r o d u c t s L L C



Envirocon Construction products L.L.C.
Abu Dhabi U.A.E.
P.O.Box :28577
Tel:+971 2 5503473
Fax:+971 2 5503474
www.enviroconcp.com

Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.