



Technical Data Sheet

Ecohard EPFC—T Epoxy Fair Coat Repair Mortar

Description

Ecohard EPFC—T is two component, solvent-free, high strength adhesive and patching compound. Formulated to give an easily applied paste high build applications particularly in vertical and overhead situations,

Ecohard EPFC—T adheres well to most building materials without the need for a primer, as well as exhibiting very good abrasion and chemical resistance.

Applications

Ecohard EPFC—T is designed for filling pinholes and surface irregularities in concrete prior to the application of subsequent coatings. It can be applied from a feather-edge up to 3 mm thickness.

- Patching repair to imperfections in concrete surfaces
- Adhesive between concrete to concrete and metal to concrete
- Filling concrete gaps and pin holes
- Sealing of surface cracks in preparation for crack injection.

Advantages

- Adhere to most of building materials without the need of primer
- bond and cure under damp conditions.
- Very good abrasion
- Solvent free, negligible-shrinkage
- Resistant to wide range of chemicals

Technical properties

Color:	Light Grey
Mixed Density	1.60 ± 0.05 kg/L
Solid content:	100%
Application Thicknesses	1-3 mm
Pot life:	70-120 minutes @ 25°C
Compressive Strength	≥65Mpa @ 7days
Application Temp.:	5 - 40 °C
Foot traffic:	24hrs @ 25°C
Full cure	7 days @25°C

Method of use

Surface preparation

All surfaces must be clean, and free of any adverse moisture conditions.

Abrasive blast to open all surface voids and remove all form oils, incompatible curing agents, hardeners, laitance, and other foreign matter and produce a surface texture similar to that of medium grit sandpaper.

Mixing

Ecohard EPFC—T is supplied in two pre-weighed packs (base and hardener).

Prior to mixing base with hardener together, stir individual components of **Ecohard EPFC—T** to disperse any separation before mixing them.

Taking care to ensure that the bottom and sides are thoroughly scraped.

Mixing should be carried out using either a forced action mixer; or a heavy duty, slow-speed drill fitted with mixing paddle.

The two components should be mixed well until a uniform consistency and color are obtained.

Application

Immediately after mixing material can be taken onto spot boards for individual applicators, trowel, scraper, filling knife and squeegee can be used depending on purpose of use (patch repair, crack filling, bonding agent...).

Ecohard EPFC—T can be overcoated with all epoxy coatings after a minimum curing period of 24 hours.

Prior to overcoating, the surface of the fully cured **Ecohard EPFC—T** should first be abraded to assist adhesion, and then cleaned to a dust-free finish.

Yield

Approx. 1.0 liter per achieve 1m² at 1.0mm

Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.



Technical Data Sheet

Ecohard EPFC—T Epoxy Fair Coat Repair Mortar

Storage

12 months when stored properly in unopened original containers in dry conditions at temperatures between 10 - 40°C.

Once the packaging has been opened, the useful life of the material is greatly reduced and it should be used as soon as possible

Cleaning

Used materials should be removed from tools, equipment and mixers with Envirocon Solvent immediately after use. Hardened material can only be removed mechanically.

Packaging

Ecohard EPFC—T is available in 4.0 Liters kit

Cautions

Health and safety

Avoid skin and eye contact by wearing overalls, gloves, goggles, and air-mask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water.

Avoid inhalation of vapors and paint mist by wearing suitable air-mask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area.

Smoking in the area should not be permitted. Local safety regulations should be followed.

Fire

Ecohard EPFC—T is non-flammable.

E n v i r o c o n C o n s t r u c t i o n P r o d u c t s L L C



Envirocon Construction products L.L.C.
Abu Dhabi U.A.E.
P.O.Box :28577
Tel:+971 2 5503473
Fax:+971 2 5503474
www.enviroconcp.com

Disclaimer:

We hope that the information herein will be helpful. The data is based upon knowledge considered to be accurate and true and is offered for the user consideration, investigation and verification in the application intended. We do not warrant the results or performance attained due to the nature of the influence of other constituent components in the application.